



Normal Specification of Maishi Monofilament Polyester Printing Mesh (Bolting Cloth)

model	mesh count	APERTURE	THREAD DIAMETER	OPENING	thickness	INK THROUGH VOLUME THEORETICALLY
	mesh/inch	micron	micron	%	micron	cm3/m2
6-400	15	1300	400	65	780-810	560
10-250	25	700	250	49	508-518	355
12-250	30	610	250	53	495-505	305
15-250	38	467	250	49	489-501	213
18-150	45	410	150	53	255-275	138
20-80	50	420	80	70	145-150	155
21-150	55	330	150	46	260-280	123
24-100	60	316	100	57	136-145	109
24-120	60	302	120	51	230-240	104
30-120	75	213	120	41	235-345	102
32-100	80	212	100	46	145-155	69
36-90	90	183	90	44	160-165	65
39-55	100	195	55	56	88-96	55.0
39-80	100	166	80	43	125-130	59.0
43-80	110	147	80	40.8	127-132	53
48-70	120	135	70	41	108-120	45.5
54-55	135	118	55	47	88-96	44.5
54-64	135	115	64	38.5	95-105	38.9
54-70	135	108	70	34	108-120	40
58-55	145	118	55	38	89-94	39.5
61-64	155	105	64	42	98-107	33
64-45	160	105	48	43	73-82	36.5
64-55	160	98	55	38	85-95	36.1
64-64	160	88	64	30	95-105	30.7
68-55	175	85	55	34	85-90	29
72-48	180	90	48	36	75-84	33.1
77-55	190	81	55	30	88-97	26.6
80-45	200	75	45	36	65-74	27.7
80-48	200	72	48	33	75-84	28.7
90-48	230	56	48	25	77-85	23.5
100-40	250	58	40	33	62-71	21.3
110-40	280	48	40	27	65-71	18.4
110-34	280	54	34	35.5	52-57	20.2
120-34	305	45	34	30.5	52-57	18.4
140-34	355	31	34	19.5	56-62	14.4
150-31	380	36	31	29	43-47	13.1
150-34	380	30	34	20.5	56-62	14.9
165-31	420	31	31	23	52-58	12.88

Notice: Other abnormal specification can be produced if the quantity more than 3000sqm

D (DENIER) =MICRON

9D=31MICRON,12D=34MICRON,16D=40MICRON,22D=48MICRON,30D=55MICRON;

40D=64MICRON, 50D=70MICRON,60D=80MICRON,80D=90MICRON,100D=100MICRON

HEBEI MAISHI WIRE MESH MANUFACTURE GROUP.

Add: NO.230, NORTH YOUYI ROAD, SHIJIAZHUANG CITY, HEBEI, CHINA

Tel:0086-311-89277936 0086-311-89277937

Fax:0086-311-85861285

0086-311-89277938 0086-311-89277939

Email:info@chinawiremesh.info

0086-311-86702978 0086-311-88890465

sales@chinawiremesh.info